



PDC® F-753

VINYL SOLVENT BASE FOR INDUSTRIAL USE ONLY

DESCRIPTION:

F-753 is a vinyl based coating used to seal unskinned polyurethane foams. F-753 can also be used on closed cell foam containing vinyl.

F-753 will produce a skin/membrane on unskinned polyurethane foam to create a barrier to moisture and chemicals. This skin has excellent resistance to fluids and petroleums. F-753 is a tough coating that adds durability to foam and imparts abrasion as well as puncture resistance.

These qualities find particular use in the medical industry, where cushioning and positioning devices are fabricated and used in sterile environments, as well as therapeutic practices. F-753 passes all types of imaging and does not artifact. Other uses include cushioning for athletic devices, seat cushions, packaging and acoustical panels. F-753 is an excellent, cost effective replacement for Hypalon® coating.

OTHER FEATURES INCLUDE:

Wide selection of colors.

Single component-no catalyst.

Passes requirements for UL94 HBF

Fast dry time.

F-753 VOC content average 2.9#/gal [see msds]

F-881 VOC content average 1.5#/gal [see msds]

SPECIFICATIONS:

Solids: (wt) 24%

Temperature use range: -0°F to 200°F

Block resistance: 4hr @ 160°F

Tensile: [ASTM D -412] 1010psi

Elongation: [ASTM D-412] 340%

Shelf life: 1+ year at 77°F

Coverage: 80 sq. ft. per gallon at 5 mils

Finish: matte-satin

Chemical resistance: In House Test Results [ASTM D-1308]

Mineral oil:	very good	Machine Oil:	very good
Saline:	very good	Blood:	very good
Urea (6% in H ₂ O):	very good	All purpose cleaner:	very good
Betadiene (Iodine):	*very good	Acid (10% sulfuric in H ₂ O):	very good
Gasoline:	good	Alcohol:	very good

*stained after 5 minutes.

ALTERNATIVE PRODUCTS:

F-830/ F-872, F-867/ F-874, refer to technical data sheets for more information.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the applications of this information or the safety and suitability of our products, either alone or in combination with other product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products whether used alone or in combination with other products. Ever changing V.O.C. regulations in your area may require you to contact local authorities for proper use and/or disposal of this product. Should you need further assistance, please contact PLASTI DIP INTERNATIONAL technical service.

PDC is a registered trademark of PLASTI DIP INTERNATIONAL
Performix and logo are trademarks of PLASTI DIP INTERNATIONAL
Hypalon is a registered trademark of DuPont, Wilmington, DE
Cowles is a registered trademark of Morehouse-COWLES, Inc.
BINKS is a registered trademark of BINKS MFG. CO., Franklin Park, IL

SURFACE PREPARATIONS:

All surfaces to be coated must be free of any oils, dust or loose foam particles.

USE ADEQUATE VENTILATION.

MIXING INSTRUCTIONS:

QUALITY CONTROL RECOMMENDATIONS FOR SPRAY AND DIP APPLICATIONS.

Like most liquid vinyls, F-753 may coagulate during storage, requiring thorough remixing agitation before use each day. For best results, a * high speed air/explosion proof electric drum mixer along with a Cowles® or dispersion blade gives the maximum combination of high shear, excellent flow and circulation. Diameters of 3" for mixing five gallon containers and 7" for mixing 50 gallon drums. Note: It has been found that the dispersion blades are highly effective, fast and produce more shearing action than can be obtained from a standard mixing blade or paddle.

After the F-753 has been agitated thoroughly, it should last 8 to 10 hours depending on your dip tank/spray equipment and temperature.

Avoid making solvent additions before mixing. Check viscosity. Some adjustments may be necessary for your particular use. Contact technical service for specific applications.

Prime coat: Set pot pressure at 20-25psi and atomizing at 30-50psi, open pattern adjustment for a 2"- 4" pattern at 6"-10" from surface. Aim spray gun at foam and fully trigger spray gun. Open material adjustment until a uniform, wet splatter appears on the foam. The wet splatter should melt or flow into the surface of the foam. Coat all sides (except bottom) with an overlapping motion. Make sure all corners and edges are thoroughly primed. The prime coat should be wet to the touch but should not completely color or cover the foam. Its purpose is to wet or prime the surface for the sealing coat, a necessity for proper adhesion.

Seal coat: After the prime coat has been applied, immediately begin sealing the foam by only partially pulling the trigger back from its previous setting until a dry, web coating appears. This seal coat should appear lighter in color than the prime coat. Hold gun approximately 6"-10" from surface and use an overlapping motion, being sure to **completely** seal the surface. If seal coat is applied too dry, poor adhesion will result. If applied too wet, sealing surface may become difficult. Again, seal all sides (except bottom), being sure to **check entire surface for complete seal.**

Finish coat: After seal coat has been applied, immediately begin applying the finish coat by fully triggering spray gun as in prime coat. Holding the gun 6"-10" from surface, apply a uniform splatter coat using an overlapping motion. Apply the finish coat as desired in thickness and texture. The finish coat is necessary to increase seal coat strength and durability. Allow the finished coated part to dry to the touch (see caution), minimum 5 minutes, then return to prime coat, seal coat and finish coat bottom of part. Follow instructions and be sure to pay close attention to corners and edges on all steps.

NOTE: To accelerate final drying, place coated object in ventilated oven at 100°F-140°F for 5 minutes. Make sure heat source is safe for this use and that you ventilate properly. To increase coating speed, you may increase atomizing pressure; open material adjustment and pattern adjustment to your comfort level.

CAUTION: It is important to apply all coatings at once. Do not allow to set more than 10-20 minutes or subject to heat. This causes an anti-block additive to come to the surface which will not allow additional coats to adhere.

* Contact Plasti Dip International Technical Service for specific equipment recommendations.

RECOMMENDED EQUIPMENT AND SETTINGS:

Binks® model 2001/ 95 gun

Nozzle: 66SS

Cap: 66SD

Needle: 565

Material: 25psi

Atomization: 30-50psi

Dilution: none required

Clean up: Acetone and Methyl Ethyl Ketone

HINTS:

Always mix before **spraying**. Avoid excessive air movement, heat or humidity. Always use proper ventilation and protection. It is required that F-881 be at 68 f or higher and mixed properly for best antiblock results.

Should you require any further information please contact us:

Plastic Dips & Coatings,

527 Bakers Creek Rd, BUNDOOK NSW 2422

Telephone: (02) 6550 2656 Fax: (02) 6550 2657

Email: sales@plastidip.net.au

REVISED 2/3/2006
PDC F-753/F-881

Plastidip.net.au